



IM-166 Series (Styrene-Butadiene)

Black Skirtboard

GENERAL PROPERTIES

- Abrasion resistant
- Flexibility
- Excellent for skirtboard applications

View Up To Date Info



◀ SCAN OR VISIT

[KOA.link/
IM-166](https://KOA.link/IM-166)

POLYMER

Styrene-Butadiene (SBR)

Series	ASTM Specification (SI units)	Temperature Range	Durometer	Tensile Strength (psi)	Elongation (%)
IM-166	ASTM D2240	-20° to 180°F (-29° to 82°C)	60 +/- 7	500 typical	300 typical

ADDITIONAL SPECIFICATIONS

Grade	Commercial
Finish	Smooth
Powder	No
Color	Black

Item Number	Gauge (in)	Width (in)	Avg. Length (Linear Ft. /Roll)	Approx. Lbs./Roll
166-04-484	1/16	48	50	90
166-08-034*	1/16	3	50	0
166-08-064*	1/16	6	50	22
166-08-094*	1/16	8	50	33
166-08-364*	1/8	36	50	134
166-08-484	1/8	48	50	178
166-08-724*	1/8	72	35	188
166-12-484*	3/16	48	50	268
166-16-034*	1/4	3	50	22
166-16-044	1/4	4	50	29
166-16-054*	1/4	5	50	37
166-16-064	1/4	6	50	44
166-16-084	1/4	8	50	59
166-16-104*	1/4	10	50	74
166-16-124	1/4	12	50	88
166-16-484	1/4	48	50	354
166-16-554*	1/4	55	40	1385
166-24-034*	3/8	3	50	33
166-24-044	3/8	4	50	44

Because we continually examine ways to improve our products, we reserve the right to alter specifications or discontinue products without prior notice.



IM-166 Series (Styrene-Butadiene)

Black Skirtboard

continued from page 15

Item Number	Gauge (in)	Width (in)	Avg. Length (Linear Ft. /Roll)	Approx. Lbs./Roll
166-24-054*	3/8	5	50	55
166-24-064	3/8	6	50	66
166-24-084	3/8	8	50	88
166-24-104*	3/8	10	50	110
166-24-124	3/8	12	50	132
166-24-484	3/8	48	50	528
166-32-034*	1/2	3	50	43
166-32-044	1/2	4	50	58
166-32-054	1/2	5	50	72
166-32-064	1/2	6	50	88
166-32-084	1/2	8	50	117
166-32-104	1/2	10	50	146
166-32-124	1/2	12	50	175
166-32-484	1/2	48	50	702
166-48-034*	3/4	3	50	66
166-48-044*	3/4	4	50	88
166-48-064	3/4	6	50	132
166-48-084	3/4	8	50	176
166-48-104*	3/4	10	50	219
166-48-124	3/4	12	50	263
166-48-484	3/4	48	50	1054
166-64-034	1	3	50	88
166-64-044*	1	4	50	117
166-64-064	1	6	50	175
166-64-084	1	8	50	234
166-64-104	1	10	50	292
166-64-124	1	12	50	351
166-64-484	1	48	50	1404
166-66-084	1 1/2	8	50	351
166-66-104	1 1/2	10	50	439
166-66-124	1 1/2	12	50	527
166-66-484*	1 1/2	48	50	2341

*Non-stocked size. Made to order with required number of rolls. Longer lead time applies. Contact Kuriyama Customer Service for details.

Maximum pieces per roll: 1 • Width tolerance: +/-0.177" • Durometer tolerance: +/-7 points

Material is within commercial sheet rubber gauge tolerances. The documentation for sheet rubber gauge tolerances is published on our website. Typical values do not constitute a specification. Please ensure the product meets your application specification prior to order placement. The website version prevails.

Because we continually examine ways to improve our products, we reserve the right to alter specifications or discontinue products without prior notice.